

FLOOR

SIERRA[™]
GLAZED CERAMIC





Create a Room that Makes a Statement If you're looking for a tile that's as attractive as it is durable, try Daltile's Sierra™ series. Subtle tone variations and a soft matte glaze create a beautiful visual effect.

· ALLURING DESIGN


- Subtle tone variations adds a beautiful visual effect to room
- Features a neutral color palette that easily coordinates into multiple designs

MULTIFACETED BEAUTY

- For added versatility, design includes five colors and two sizes




FIELD TILE



RAINIER 1500







ALMOND 2009 ASPEN 1525 BLACK 2011

SIERRA™

GLAZED CERAMIC

SIZES

		Thickness	Sq. Ft. per Carton	Pieces per Carton
	(11-13/16" x 11-13/16") (30.00 cm x 30.00 cm)	5/16"	11.00	11
8 x 8 Field Tile	(7-7/8" x 7-7/8") (20.00 cm x 20.00 cm)	5/16"	11.00	25

FLOOR APPLICATIONS

	Target DCOF wet	Suitable
Dry & Level – Interior	N/A	~
Wet & Level – Interior	≥ 0.42	
Exterior Applications; Pool Decking & Other Wet Areas with Minimal Footwear	≥ 0.60	
Ramps & Inclines	≥ 0.65	

A DCOF value of \geq 0.42 is the new standard for tiles specified for commercial application in standard A137.1–2012, Section 9.6. It replaces the SCOF value of \geq 0.60 referenced in ASTM C1028. For more information on the correlation between the two values and about the DCOF AcuTest", visit www.daltile.com/dcof.

OTHER APPLICATIONS

	Suitable
Walls/Backsplashes	✓
Countertops	✓
Pool Linings	

APPLICATION NOTES:

Suitable for exterior applications in non-freezing climates only when proper installation methods are followed.

TRIM

Туре	Number	Size	Pieces per Carton
Bullnose	P-43C9	3 x 12	22

Bullnose trim is intended to coordinate with floor field tile in the standard 90-degree installation position.

INSTALLATION

Grout Joint Recommendation	Shade Variation
3/16"	Low (V1)

TEST RESULTS

	ASTM#	Result
Water Absorption	C373	< 7.0%
Breaking Strength	C648	> 250 lbs.
Scratch Hardness	MOHS	7.0
Chemical Resistance	C650	Resistant

NOTES

Manufacturer Warning: These tiles have a dynamic coefficient of friction less than 0.42 as measured by the DCOF Acutest method. Tiles with DCOF Acutest values less than 0.42 are not recommended for use in areas with wet or slippery conditions. If such tiles are used as a walking surface where water, ice, oil, grease and/or other substances are present, such a condition could cause a reduction in foot traction and become unexpectedly slippery resulting in a fall or personal injury. See ANSI standard A137.1 section 6.2.2.1.10, available at www.tileusa.com.

Use of a latex modified thin-set is recommended for proper installation.

Since there are variations in all fired ceramic products, tile and trim supplied for your particular installation may not match these samples. Final color selection should be made from actual tiles and trim and not from tile samples or color reproductions. Manufactured in accordance with ANSI A137.1 standards.

Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.

For additional information refer to "Factors to Consider" at daltile.com/Factors.



visit daltilegreenworks.com.



