

TILE & STONE

RANGE
porcelain



121 Calacatta



151 Statuario



150 Bianco



155 Zebrino



200 Allure



500 Argento



550 Ash

RANGE POLISHED

Nano sealed — does not require sealing on most normal applications

Uses the chemical method as described above. Suitable for most residential, but commercial may benefit from a sealer application. Sealer recommended if using a high-performance or contrasting grout color.

TILE & STONE

Style Number	CS35W	CS39W	CS34W	CS30Z	CS37W	CS31Z	CS32Z	CS33Z
Construction	porcelain	porcelain	porcelain	porcelain	porcelain	porcelain	porcelain	porcelain
Tile Type	floor tile	floor tile polished	floor tile	floor tile polished	bullnose	bullnose polished	basketweave mosaic	mosaic polished
Tile Size	16" x 32"	16" x 32"	12" x 24"	12" x 24"	3" x 12"	3" x 12"	12" x 12" x 2"	12" x 12" x 2"
Edges	rectified	rectified	rectified	rectified	rectified	rectified	rectified	rectified

Technical

Wear Rating Group	4	4	4	4	4	4	4	4
Break Strength	> 450	≥ 500	> 450	≥ 500	> 450	≥ 500	> 450	500
Water Absorption %	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5
DCOF	≥ 0.42	< 0.42	≥ 0.42	< 0.42	≥ 0.42	< 0.42	≥ 0.42	< 0.42
Shade Variation	V2	V2	V2	V2	V2	V2	V2	V2
Installation Area	Floors, Walls, Exteriors	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*


*exterior wall only for polished product

A DCOF value of > 0.42 is the new standard for tiles specified for commercial application in standard A1371-2012, Section 9.6. It replaces the SCOF value of > 0.60 referenced in ASTM C1028. For more information on the correlation between the two values and about the DCOF AcuTest visit the Tile Council of North America's website: www.tcnatile.com


MANUFACTURER'S WARNING:

- Tiles with DCOF AcuTest values less than .42 are not recommended for use in areas with wet or slippery conditions. If such tiles are used as a walking surface where water, ice, oil, grease and/or other substances are present, such a condition could cause a reduction in foot traction and become unexpectedly slippery resulting in a fall and personal injury. See ANSI standard A1371 section 6.2.2.1.10, available at www.tcnatile.com/sections6.2.2.1.10.html.
- Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.
- Since there is a shade variation on all natural products, the tile and trim supplied for your particular installation may not match these samples. Final selection should be made from actual tiles and trim and not from tile and trim samples or color reproductions. Manufactured in accordance with ANSI A1371 standards.


Colors



121 Calacatta




150 Bianco




151 Statuario



155 Zebrino



200 Allure



500 Argento



550 Ash

