TILE & STONE

EMBERWOODporcelain



571 Carbon





Shaw

EMBERWOOD

TILE & STONE

Style Number	CS69Z	CS70Z	CS72Z	CS92Z
Construction	porcelain	porcelain	porcelain	porcelain
Tile Type	floor tile	floor tile	bullnose	herringbone mosaic
Tile Size	7"×47"	2.5"×16"	2.5"×16"	11" × 13.5"
Technical				
Wear Rating Group	4	4	4	4
Break Strength	> 400	> 400	> 400	> 400
Water Absorption %	< 0.5	< 0.5	< 0.5	< 0.5
DCOF	> 0.5	> 0.5	> 0.5	> 0.5
Shade Variation	V3	V3	V3	V3
Installation Area	Floors, Walls, Exteriors	Floors, Walls, Exteriors	Floors, Walls, Exteriors	Floors, Walls, Exteriors


A DCOF value of >0.42 is the new standard for tiles specified for commercial application in standard A137.1-2012, Section 9.6. It replaces the SCOF value of >0.60 referenced in ASTM C1028. For more information on the correlation between the two values and about the DCOF AcuTest visit the Tile Council of North America's website: www.tcnatile.com

MANUFACTURER'S WARNING:

- Tiles with DCOF AcuTest values less than 0.42 are not recommended for use in areas with wet or slippery conditions. If such tiles are used as a walking surface where water, ice, oil, grease and/or other substances are present, such a condition could cause a reduction in foot traction and become unexpectedly slippery resulting in a fall and personal injury. See ANSI standard A137.1 section 6.2.2.1.10, available at www.tcnatile.com/sections6.2.2.1.10.html.
- Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.
- Since there is a shade variation on all natural products, the tile and trim supplied for your particular installation may not match these samples. Final selection should be made from actual tiles and trim and not from tile and trim samples or color reproductions. Manufactured in accordance with ANSI A137.1 standards.

Colors

510 Ash





571 Carbon



719 Burned



571 Carbon



719 Burned





