



121 Calacatta



155 Zebrino



151 Statuario

# CASINO POLISHED

Nano sealed — does not require sealing on most normal applications

Uses the chemical method as described above. Suitable for most residential, but commercial may benefit from a sealer application. Sealer recommended if using a high-performance or contrasting grout color.

# TILE & STONE

Style Number	CS37V	CS88Z	CS89Z	CS87Z	CS36V	CS35V
<b>Construction</b>	porcelain	porcelain	porcelain	porcelain	porcelain	porcelain
<b>Tile Type</b>	floor tile polished	floor tile matte	floor tile polished	floor tile matte	floor tile polished	floor tile polished
<b>Tile Size</b>	24" × 24"	16" × 32"	16" × 32"	12" × 24"	12" × 24"	4" × 12"
<b>Edges</b>	rectified	rectified	rectified	rectified	rectified	rectified

## Technical

<b>Wear Rating Group</b>	4	4	4	4	4	4
<b>Break Strength</b>	≥ 500 lbs.	≥ 500 lbs.	≥ 500 lbs.	> 450 lbs.	≥ 500 lbs.	≥ 500 lbs.
<b>Water Absorption</b>	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5
<b>DCOF</b>	< 0.42	> 0.42	< 0.42	> 0.42	< 0.42	< 0.42
<b>Shade Variation</b>	V2	V2	V2	V2	V2	V2
<b>Installation Area</b>	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*	Floors, Walls, Exteriors*

\*exterior wall only for polished product

A DCOF value of >0.42 is the new standard for tiles specified for commercial application in standard A1371-2012, Section 9.6. It replaces the SCOF value of >0.60 referenced in ASTM C1028. For more information on the correlation between the two values and about the DCOF AcuTest visit the Tile Council of North America's website: [www.tcnatile.com](http://www.tcnatile.com)

### MANUFACTURER'S WARNING:

- Tiles with DCOF AcuTest values less than 0.42 are not recommended for use in areas with wet or slippery conditions. If such tiles are used as a walking surface where water, ice, oil, grease and/or other substances are present, such a condition could cause a reduction in foot traction and become unexpectedly slippery resulting in a fall and personal injury. See ANSI standard A137.1 section 6.2.2.1.10, available at [www.tcnatile.com/sections6.2.2.1.10.html](http://www.tcnatile.com/sections6.2.2.1.10.html).
- Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.
- Since there is a shade variation on all natural products, the tile and trim supplied for your particular installation may not match these samples. Final selection should be made from actual tiles and trim and not from tile and trim samples or color reproductions. Manufactured in accordance with ANSI A137.1 standards.

## Colors



121 Calacatta



151 Statuario



\*155 Zebrino (not available in CS37V)



200 Allure



500 Stella





500 Stella



121 Calacatta

# CASINO POLISHED

Nano sealed — does not require sealing on most normal applications

Uses the chemical method as described above. Suitable for most residential, but commercial may benefit from a sealer application. Sealer recommended if using a high-performance or contrasting grout color.

# TILE & STONE

Style Number	CS90Z	CS38V	CS91Z	CS40V	CS39V
<b>Construction</b>	porcelain	porcelain	porcelain	porcelain	porcelain
<b>Tile Type</b>	bullnose matte	bullnose polished	basketweave polished	basketweave matte	hexagon mosaic polished
<b>Tile Size</b>	2.75" x 12"	2.75" x 12"	12" x 12" x 2"	12" x 12" x 2"	11.5" x 12"

## Technical

<b>Wear Rating Group</b>	4	4	4	4	4
<b>Break Strength</b>	≥ 500 lbs.	≥ 500 lbs.	≥ 500 lbs.	≥ 500 lbs.	≥ 500 lbs.
<b>Water Absorption</b>	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5	≤ 0.5
<b>DCOF</b>	> 0.42	< 0.42	< 0.42	≥ 0.42	< 0.42
<b>Shade Variation</b>	V2	V2	V2	V2	V2
<b>Installation Area</b>	Floors, Walls, Exteriors*	Floors, Walls, Exteriors*	Floors, Walls, Exteriors*	Floors, Walls, Exteriors	Floors, Walls, Exteriors*

\* exterior wall only for polished product

A DCOF value of >0.42 is the new standard for tiles specified for commercial application in standard A1371-2012, Section 9.6. It replaces the SCOF value of >0.60 referenced in ASTM C1028. For more information on the correlation between the two values and about the DCOF AcuTest visit the Tile Council of North America's website: [www.tcnatile.com](http://www.tcnatile.com)

### MANUFACTURER'S WARNING:

- Tiles with DCOF AcuTest values less than 0.42 are not recommended for use in areas with wet or slippery conditions. If such tiles are used as a walking surface where water, ice, oil, grease and/or other substances are present, such a condition could cause a reduction in foot traction and become unexpectedly slippery resulting in a fall and personal injury. See ANSI standard A1371 section 6.2.2.1.10, available at [www.tcnatile.com/sections6.2.2.1.10.html](http://www.tcnatile.com/sections6.2.2.1.10.html).
- Water, oil, grease, etc. create slippery conditions. Floor applications with exposure to these conditions require extra caution in product selection. Not for use on ramps.
- Since there is a shade variation on all natural products, the tile and trim supplied for your particular installation may not match these samples. Final selection should be made from actual tiles and trim and not from tile and trim samples or color reproductions. Manufactured in accordance with ANSI A1371 standards.

## Colors

### CS39V hexagon mosaic




121 Calacatta



151 Statuario



155 Zebrino



200 Allure



500 Stella

### CS40V basketweave mosaic



121 Calacatta



151 Statuario



155 Zebrino



200 Allure



500 Stella

